# Polypropylene BALEN 01270

## PRODUCT DESCRIPTION

BALEN 01270 is a propylene homopolymer obtained in the presence of a complex organometallic catalyst. It is characterized by resistance to thermal-oxidative aging.

#### APPLICATION

Textured and non-textured yarns, fine staple fibers, food contact articles, toys.

	ı	I
Parameter name	Value	Test method
Melt flow index (230 °C/2.16 kgf), g/10 min	22-30	GOST 11645, ASTM D 1238
Spread of melt flow index values within a batch, %, no moree	± 10	TC 2211-074- 05766563-2015
Mass fraction of volatile substances, %, no more	0.09	TC 2211-074- 05766563-2015
Tensile yield strength, MPa, no less	Not standardized	GOST 11262, ASTM D 638
Relative elongation at yield strength, %, no less	Not standardized	GOST 11262, ASTM D 638
Bending modulus, MPa, no less	Not standardized	ASTM D 790
Mass fraction of isotactic fraction, %	94	TC 2211-074- 05766563-2015
Resistance to thermal-oxidative ageing at 150 °C, h, no less	360	TC 2211-074- 05766563-2015

# TC 2211-074-05766563-2015 with amendments 1-6

## HAZARD IDENTIFICATION

At room temperature, the polymer does not emit toxic substances into the environment and does not have a harmful effect on the human body upon direct contact. The product aerosol is classified as a moderately hazardous substance in terms of its effect on the body and has weakly expressed irritating properties. Balen belongs to the group of solid flammable materials with high smoke-forming capacity. Thermal decomposition products are toxic. Balen may have an impact on the environment if handling rules are violated.

FORM OF PRODUCT	Stabilized, uncolored, in the form of granules ranging in size from 2 to 5 mm.
PACKAGE	Polyethylene bags with welded neck; net weight of product in the bag $25.0\pm0.3$ kg. It is allowed to pack bags on flat pallets using heat-shrinkable film. Gross weight of the package up to 2 tons.
	Transported by all types of transport in covered vehicles in accordance with the rules for the carriage of goods applicable to this type of transport.
TRANSPORTATION AND STORAGE	Stored in a closed, dry room, excluding direct sunlight, at a distance of at least 1 m from heating devices at a temperature no higher than 30°C, relative humidity no more than 80%.  Storage at the consumer's is allowed for up to 30 days in metal storage containers installed on outdoor platforms, excluding moisture ingress and contamination of the products.
GUARANTEE OF MANUFACTURER	Guaranteed shelf life - 3 years from date of manufacture.

The information contained in this document is given according to our knowledge at the time of publication. It is the responsibility of the customer to test our products to determine their suitability for the intended application. The manufacturer accepts no liability for loss/damage that may arise from the use of this information. UN number: none. Classification code: none.

